



EQ-6180

Carbon Nano Gel Bloc





Electrical Specifications

Voltage	6V	
M.R.C. 25 Amps	435	
80% DOD Voltage Cutoff	5.6V	
Self Discharge	Less than 3% per month (20°C/68°F)	
Charge Temperature	Min: -10°C (14°F) / Max: 50°C (122°F)	
Discharge Temperature**	Min: -40°C (-40°F) / Max: 50°C (122°F)	
Storage	Min: -20°C (-4°F) / Max: 60°C (140°F)	

Cell Type Ue	C5	C10	C20	C100
(100%) / VPC	1.70	1.75	1.75	1.80
Ref Temp	25°C	25°C	25°C	25°C
EQ-6180	184	198	210	225

 $^{{}^{**}\}text{CAUTION: Depths of discharge, operating voltages and currents, when designing systems for use at maximum temperatures, will vary.}\\$

Mechanical Specifications


Industry Reference		-	
Length (A)	9.57 in	243 mm	
Width (B)	7.36 in	187 mm	
Height (C)	10.79 in	274 mm	
Weight	71 lbs	32 kgs	
Terminal (Opt'l)*	M8		
Cell(s)	3		
Electrolyte	Gel		
Terminal Torque Nm	8		

NOTE: There is a tolerance of +/-2%.

Terminal Options Available:

M8 A-Pole





Features

Maintenance free - no topping up required

Ultra energy efficient due to low resistance

Reduced operating temperatures for increased cycle life (up to 1000 cycles) and battery lifetime

Cost savings due to increased efficiency

Up to 2 x faster recharge

Increased design life from 12 to 15 years

Allows for opportunity charging to give you those extra running times when required

Suitable for extreme temperature variants

Applications: all motive, leisure & solar:

Electric vehicles, including cleaning machines

Wheelchairs

Electric Working Platforms

UPS Systems

Traffic Systems

Telecommunications & Emergency Lighting

Caravans / Motorhomes RV's & Maritime

Solar & Renewable Energy & Home Invertor



Charging profile

IU Charging $I = min. 12\% C_5 max. 30\% C_5$


U = 2.4 V per cell

IUI Charging $I_1 = min. 12\% C_5 max. 40\% C_5$

 $U = 2.35 \, \text{V} \, \text{per cell}$

 $I_2 = 1.5 \% C_5$ for max. 4 hours

Self discharge at different temperatures




Capacity vs. temperature

10°C


20°C

30°C


40°C



Storage: Determine the state of charge



Relation between charging, voltage and temperature



STANDBY USE

CYCLE USE